



## FJlab-TDS

Ref.n° : 29092013-001  
Issue date:  
Print date: 13/06/2017



## TDS Tuttofare Touch

Product code:

Product type:

App:

Composition: 59% Viscose - 34% Polyester - 7% Synthetic resins

Characteristic	Test Method	Units	Values	Range
Basis Weight	Edana ERT 40.3-90	Gr.mtq	140	10% +/-
Absorption	Edana 10.3-99	%	730	10% +/-
Thickness	Edana ERT 30.55-99	mm	1,4	10% +/-
MD Tensile Strength	Edana ERT 20.2-89	N	130	10% +/-
MD Elongation at Break	Edana ERT 20.2-89	%	35	10% +/-
CD Tensile Strength	Edana ERT 20.2-89	N	110	10% +/-
CD Elongation at Break	Edana ERT 20.2-89	%	60	10% +/-
Rigidity MD	Edana 50.5-99	mN cm	1380	10% +/-

**Fa-Ma Jersey Spa**

Via Settola 22 – 51100 Pistoia Italy - Tel +39 0573 445501 – Fax +39 0573 534440

[www.famajersey.com](http://www.famajersey.com) [info@famajersey.com](mailto:info@famajersey.com)